

Durham Research Online

Deposited in DRO:

21 July 2020

Version of attached file:

Accepted Version

Peer-review status of attached file:

Peer-reviewed

Citation for published item:

Bunga, Yousillya and Katakya, Ritu (2020) 'Real time monitoring of interactions of gold nanoparticles with supported phospholipid lipid layers.', *Journal of electroanalytical chemistry.*, 872 . p. 114302.

Further information on publisher's website:

<https://doi.org/10.1016/j.jelechem.2020.114302>

Publisher's copyright statement:

© 2020 This manuscript version is made available under the CC-BY-NC-ND 4.0 license
<http://creativecommons.org/licenses/by-nc-nd/4.0/>

Additional information:

Use policy


The full-text may be used and/or reproduced, and given to third parties in any format or medium, without prior permission or charge, for personal research or study, educational, or not-for-profit purposes provided that:

- a full bibliographic reference is made to the original source
- a [link](#) is made to the metadata record in DRO
- the full-text is not changed in any way

The full-text must not be sold in any format or medium without the formal permission of the copyright holders.


Please consult the [full DRO policy](#) for further details.

Supplementary Material:



ESI Figure S1: Schematic illustration of the various types of NPs-membrane interactions; A) charged NPs approaching liposome (surface of lipid bilayer membrane), B) adhesion of NPs onto membrane surface, C) defect (pore) formation caused by NPs and D) NP encapsulation inside liposome. ¹


a




ESI Figure S2: Structures of (a) 2-oleoyl-1-palmitoyl-sn-glycero-3-phosphocholine (POPC), (b) 1,2-dipalmitoyl-sn-glycero-3-phosphothioethanol (DPSTE), (c) 1-dodecanethiol, (d) 6-(ferrocenyl)hexanethiol

ESI Section 1 : RESI technique & illustration

A




B




ESI Figure S3 A) Bode plot (phase angle α , impedance $|Z|$) to illustrate the effect of the inductive impedance (Z_L) connected in parallel with the sensor (circuit diagram II) and without it (circuit diagram I). A sharp resonance peak appears in the spectrum; the frequency of the peak varies with the capacitance C. B) An illustration of the z-LAB circuitry for the integrated sensor chip.

The integrated sensor chip is represented by an internal impedance Z_c , which is connected in parallel with an inductive impedance L (Figure S1B). The principal components of the sensor comprised resistors (R) and capacitors (C). The working electrodes on the sensor are immersed in the flow cell and can be connected to the reference electrode (RE) and counter electrode (CE). ²



ESI Figure S4: Transmission electron microscopy (TEM) images of thiolated gold nanoparticles; A) DDT-AuNPs, B) 5nm FcHT-AuNPs, C) 10 nm FcHT-AuNPs and D) 20 nm FcHT-. AuNPs



ESI Figure S5: AFM images in tapping mode and height profiles of

A : Height profile of a lipid modified substrate with no Au NPs

B and B' : Height profile and AFM image of lipid modified substrate in contact with DDTAuNpS for 1 h

C and C' : Height profile and AFM image of lipid modified substrate in contact with DDTAuNpS for 1 h

All images are 200 x 200 nm. [DDT-AuNPs] = 1.2 nM.

ESI Section 2

Theoretical calculation of number of ligands per nanoparticle.

Assuming that all particles are completely spherical and using the determined TEM diameter (D), the number of metal atoms per NP (N) was determined using the equation below from Liu and co-workers¹.

$$N = \frac{\pi \rho D^3}{6 M} \quad (\text{A1})$$

The atomic molar mass of the metal (M , Au = 197 g mol⁻¹) and the density of face-centered cubic (fcc) of the metal (Au = 19.3 g cm⁻³).

Table SI1a. Determination of the number of atoms and ligands per NP.

Ligand	Average number of Au atoms
DDT	6.57×10^2
FcHT	5.20×10^3

Theoretical calculation of the molar concentration of NPs in the solution

The calculations for the molar concentration of the NPs (C) were adapted from Kalishwaralal and co-workers³ using the equation below, assuming that 100% reduction of salt HAuCl_4 for AuNPs to Au atoms


$$C = \frac{N_{\text{Total}}}{NVN_A} \quad (\text{A2})$$

The total number of metal atoms added i.e. the initial amount of salt (AgNO_3 for AgNPs and HAuCl_4 for AuNPs) added to the reaction (N_T , M), the number of metal atoms per NP determined from Eq. 3 (N) and the volume of the reaction solution (V , L).


Table 1b. Determination of the molar concentration of NPs.

Ligand	Molar concentration of AuNPs / μM
DDT	3.38×10^2
FcHT	4.11

Further required concentrations were made out from the initial concentration determined above.



ESI Figure S6: CV of bare vs lipid-modified gold electrodes (0.02 cm^2) in solution of $10 \text{ mM Fe}^{3+}/4^+$ in 0.1 M KNO_3 at 50 mV/s scan rate showing formation of SAM and BLM on the electrode surface.



ESI Figure S7: DPVs of the SAM-modified gold electrode in 0.1 M KNO₃ at 60, 240, 960 and 1800 min immersion times in FcHT-AuNPs. Sweep amplitude: 5 mV/s. [FcHT-AuNPs] = 2.8 μM.




Fig ESI S8: DPVs of the electrochemical response of lipid modified gold electrodes after incubation in FcHT-AuNPs after 60 min in 0.1 M phosphate buffer at a potential of -0.1 V. The electrodes were taken out of the buffer solution, rinsed and DPV measurements in both forward and backward directions were taken in a background of 0.1 M NaClO₄ at 100 mV/s scan rate. Sharp desorption peaks were observed, in the scans in the negative direction, at approximately 0.4 V,

References:

1. X. Liu, M. Atwater, J. Wang and Q. Huo, *Colloids Surf. B Biointerfaces*, 2007, **58**, 3–7.
2. A. Lundgren, J. Hedlund, O. Andersson, M. Brändén, A. Kunze, H. Elwing, F. Höök, . Resonance-Mode Electrochemical Impedance Measurements of Silicon Dioxide Supported Lipid Bilayer Formation and Ion Channel Mediated Charge Transport., *Anal. Chem.* 83 (2011) 7800–7806. <https://doi.org/10.1021/ac201273t>.
- 3 K. Kalishwaralal, S. Barath ManiKanth, S. R. K. Pandian, V. Deepak and S. Gurunathan, *Colloids Surf. B Biointerfaces*, 2010, **79**, 340–344.